

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15

(BSP December 2, 2002)
Placing Patching Concrete For Polyester Concrete Overlay
Patching concrete shall be polyester concrete, as specified in Section 6-09.3(3) as supplemented in these Special Provisions. Concrete Class M shall not be used.

Polyester concrete for deck repair shall be placed and cured in accordance with Sections 6-09.3(11) and 6-09.3(13), respectively, as supplemented in these Special Provisions.

All deck repair material that fails to achieve a minimum compressive strength of 20 MPa in six hours as verified by the rebound number determined in accordance with ASTM C 805 shall be removed and replaced with new deck repair material by the Contractor, at no additional expense to the Contracting Agency.